

## RECKLI<sup>®</sup> EcoSil 25

RECKLI EcoSil 25

Product 03367

Edition 01/23

**Silicone moulding material for single use**

### PROPERTIES

RECKLI EcoSil 25 is a castable, elastic two-component silicone rubber, cold curing by polycondensation and self-releasing. On mouldings even finest surface contours and textures are reproduced. The adjustment of a thixotropic consistency by RECKLI Si-Thickener Liquid is not possible.

### APPLICATIONS

RECKLI EcoSil 25 is used for making self-releasing elastic moulds for single use. It is not suitable for permanent usage in ceramic-, construction-, electro- or candle-industry.

#### Attention!

Moulds out of RECKLI two-component silicones are not fully suitable for casting polyester- or PMMA-resins. These applications strictly demand a preliminary test.

### TECHNICAL DATA

property	value	method
hardener:	Si-Hardener Type N	
mixing ratio (base : hardener):	10 : 1	(according to weight)
workable temperature:	+10 °C – +30 °C	
viscosity of base component:	15000 mPa·s	ISO 2555
viscosity of mixture:	10000 mPa·s	ISO 2555
pot life (200-g-mixture at +21 °C):	15 – 25 min	
earliest demoulding (at +21 °C):	2 h	
specific weight:	1,3 g/cm <sup>3</sup>	
hardness:	23 Shore A	DIN 53505
tensile strength:	1,5 N/mm <sup>2</sup>	DIN 53504-S2
elongation at break:	200 %	DIN 53504-S2
tear resistance:	1,5 N/mm	ASTM D 624-B
heat resistance (dry heat):	approx. +150 °C	
linear shrinkage:	0,5 – 0,8 %	
colour:	beige	
odour:	weak	

These data are typical guide values. They are not destined for the generation of specifications.

RECKLI GmbH

Industriestraße 36

D-44628 Herne

Tel +49 2323 1706-0

Fax +49 2323 1706-50

info@reckli.de

www.reckli.de

## SURFACE PREPARATION

The model surface must be clean. Absorbing surfaces should preferably be sealed to avoid contamination by silicone oil and to ensure the easiness of the subsequent demoulding. For this, RECKLI PUR-Sealant can be used if the surface is solvent-resistant. Otherwise, especially if the surface has to be recovered in the original state, RECKLI Si-Stripping Lacquer can be applied and removed with water along with all residues after completing the moulding works. Before continuing, the sealant has to dry completely. Further measures are usually unnecessary due to the self-releasing effect. However, certain critical substrates, in particular glass, freshly milled metal or wood as well as silicone itself, must be covered with RECKLI Mould Wax. When applying silicone in several layers, even after the surface is completely cured, the adhesion of the following layer to the substrate is perfect.

RECKLI EcoSil 25  
Product 03367  
Edition 01/23

## PROCESSING

Before processing, the base component has to be stirred up thoroughly. Add the hardener (B) to the base component (A) and mix them homogenously. Transfer the mixture into a second receptacle and stir it up again. Thereby the incorporation of larger amounts of air should be avoided. Once mixed, the processing of the material must be completed within the pot life (15 – 25 minutes). The shortest demoulding time is 2 hours.

## METHOD OF PROCESSING

Full cast.

## CLEANING OF EQUIPMENT

For the cleaning of the tools and the equipment, use dry, absorbing cloths, if necessary RECKLI EK-PU Thinner in addition. Immersion in solvents is not sufficient. When cured, the material can be removed from the tools due to the self-releasing effect.

## PACKAGING SIZES

double drums: 5 kg | double cans: 1 kg.

The hardener is enclosed in the lid.

## STORAGE

Store in a dry place at room temperature. RECKLI EcoSil 25 is storable for 6 months from delivery when kept in the closed original packaging at about 18 °C. Opened drums must be closed airtight right after use.

## GENERAL INFORMATION

For further information please also see:

RECKLI GmbH  
Industriestraße 36  
D-44628 Herne  
Tel +49 2323 1706-0  
Fax +49 2323 1706-50  
info@reckli.de  
www.reckli.de

„General advice for making moulds and models using RECKLI two-component silicones “.

## **SAFETY**

Protect skin and eyes from material splashes. Please consult the relevant safety data sheet and attend to the indications on the label of the package regarding the Dangerous Goods Regulation. This pamphlet is intended solely as an application directive. It does not claim to be binding and valid for all modes of application. A preliminary test under operation conditions is highly recommended.

This pamphlet replaces all previously published pamphlets concerning RECKLI EcoSil 25, stating them as no longer being valid.

RECKLI EcoSil 25

Product 03367

Edition 01/23

**RECKLI GmbH**

Industriestraße 36

D-44628 Herne

Tel +49 2323 1706-0

Fax +49 2323 1706-50

info@reckli.de

www.reckli.de