

PRELIMINARY TECHNICAL PAMPHLET

RECKLI[®] PUR-Sealant LI

RECKLI PUR-Sealant LI

Product 07064

Edition 02/24

one-component polyurethane sealant

PROPERTIES

RECKLI PUR-Sealant LI is a liquid, solvent-containing, ready for use one-component polyurethane sealant with high solid content. It hardens in contact with humidity. When dried, it shows high abrasion-resistance, high impact resistance and high chemical resistance. On exposure to light, particularly direct sunlight, it is not resistant against yellowing. However, its chemical and mechanical properties are not affected thereby.

RECKLI PUR-Sealant LI contains monomer diisocyanates at a level below 0,1 % (according to weight). Thus, it is exempt from restriction and training obligation according to REACH, annex XVII, No. 74.

APPLICATIONS

RECKLI PUR-Sealant is particularly suitable for sealing formwork panels or slabs to improve wear-resistance and durability. Furthermore, it is used for the surface preparation of solvent-resistant moulds and models when making moulds out of RECKLI polyurethane or silicone elastomers.

RECKLI PUR-Sealant LI is not applicable on non-absorbent surfaces, such as metal, plastic, ceramics, artificial stone or certain kind of natural stone.

TECHNICAL DATA

property	value	method
appearance:	light yellow, transparent liquid	
density:	1,04 g/cm ³	ISO 2811
solid content:	40 %	by weight
flash point:	approx. 28 °C	DIN 51755
workable temperature:	+5 °C – +30 °C	
dust-dry after:	30 – 40 min	
tack-free after:	approx. 90 min	
earliest recoatability:	2 h	
latest recoatability:	24 h	
earliest mechanical loading:	6 h	
full chemical and mechanical loading after:	7 days	

RECKLI GmbH

Industriestraße 36

D-44628 Herne

Tel +49 2323 1706-0

Fax +49 2323 1706-50

info@reckli.de

www.reckli.de

These data are typical guide values. They are not destined for the generation of specifications.

RECKLI PUR-Sealant LI

Product 07064

Edition 02/24

SURFACE PREPARATION

The substrate must be absorbent, stable, sound, dry, clean and free of oil, grease or wax. Cement laitance has to be removed by grinding or by the use of acids. In case of doubt, we recommend the preparation of a representative test area.

PROCESSING

For priming, RECKLI PUR Sealant LI can be diluted with RECKLI EK-PU-Thinner up to 50 %, depending on the surface's absorbency. On highly absorbent substrates, it is recommended to apply RECKLI PUR Sealant LI un- or weakly diluted. Vice versa, it should be used in a higher dilution on less absorbent surfaces.

PUR-Sealant LI should be applied in several thin layers by brush, paint roller or rubber blade. The application of thick layers or the formation of puddles causes rough surfaces, bubbles or craters.

CONSUMPTION

Approx. 100 –200 g/m² per application, depending on the type of structure.

CLEANING OF EQUIPMENT

The tools and the equipment can be cleaned with RECKLI EK-PU Thinner. Immersion in solvents is not sufficient.

PACKAGING SIZES

cans: 5 kg | tins: 1 kg.

STORAGE

Store in a dry, well ventilated place at room temperature. Keep the container tightly closed; do not expose to direct sun irradiation. Keep away from any sources of ignition, do not smoke. RECKLI PUR-Sealant LI is storable for 6 months from delivery when kept in the closed original packaging at about 18 °C. Opened drums must be closed airtight right after use. Partial amounts, once taken from the package, must not be returned into the container.

VOC COMPLIANCE STATEMENT

RECKLI PUR-Sealant LI is not permitted for applications that are subject to Directive 2004/42/EU, as listed in annex 1.I.

GENERAL INFORMATION

For further information please also see:

RECKLI GmbH

Industriestraße 36

D-44628 Herne

Tel +49 2323 1706-0

Fax +49 2323 1706-50

info@reckli.de

www.reckli.de

„ General advice for the processing of RECKLI two-component resins”.

SAFETY

PUR-Sealant LI contains solvents and isocyanates. Provide sufficient ventilation in the working place. Keep away from heat, sparks, open flames or any other ignition sources. Do not smoke! Avoid breathing gas or vapours. Do not use for sputtering or spraying. Protect skin and eyes from material splashes. Provide sufficient ventilation in the working place. Please consult the relevant safety data sheet and attend to the indications on the label of the package regarding the Dangerous Goods Regulation. This pamphlet is intended solely as an application directive. It does not claim to be binding and valid for all modes of application. A preliminary test under operation conditions is highly recommended.

This pamphlet replaces all previously published pamphlets concerning RECKLI PUR-Sealant LI, stating them as no longer being valid.

RECKLI PUR-Sealant LI

Product 07064

Edition 02/24

RECKLI GmbH

Industriestraße 36

D-44628 Herne

Tel +49 2323 1706-0

Fax +49 2323 1706-50

info@reckli.de

www.reckli.de